

Spilltration® Husky Material Specifications

TEST	METHOD	UNITS	RESULT
Thickness		in (mm)	0.59 (15)
Mass Per Unit Area	ASTM 5261	oz/yd2 (g/m2)	20.5 (695)
Grab Tensile MD	ASTM D-4632	lbs (kg)	22.9 (10.4)
Grab Tensile TD	ASTM D-4632	lbs (kg)	33.4 (15.1)
Elongation at Peak MD	ASTM D-4632	percent	25%
Elongation at Peak TD	ASTM D-4632	percent	25%
Trapezoid Tear Strength MD	ASTM D-4533	lbs (kg)	29.4 (13.3)
Trapezoid Tear Strength TD	ASTM D-4533	lbs (kg)	43.5 (19.7)
Apparent Opening Size	ASTM D-4751	Microns	53
Puncture Resistance	ASTM D-4833	lbs (kg)	31.3 (14.19)
Bursting Strength	ASTM D-3786	lbs/in2 (kg/cm2)	159 (11.1)
Permittivity	ASTM D-4491	sec-1	1.834
Average Permeability	ASTM D-4491	cm/sec	1.79
Flow Rate	ASTM D-4491	gal/ft2/min (l/m2/min())	137.4 (5,598.4)
Hydrocarbon Capacity		gal/yd2 (l/m2)	2.5 (11.3)



HalenHardy®, LLC
 305 Main Street
 Bellwood, PA, USA 16617

sales@HalenHardy.com
 www.HalenHardy.com
 814-822-2004