



Spilltration® materials are
manufactured exclusively by HalenHardy®

Spilltration® Husky Polyback Material Specifications

TEST	METHOD	UNITS	RESULT
Thickness		in (mm)	0.59 (15)
Mass Per Unit Area	ASTM 5261	oz/yd2 (g/m2)	21.5 (731)
Grab Tensile MD	ASTM D-4632	lbs (kg)	61 (27.66)
Grab Tensile TD	ASTM D-4632	lbs (kg)	68 (30.84)
Elongation at Peak MD	ASTM D-4632	percent	30%
Elongation at Peak TD	ASTM D-4632	percent	45%
Trapezoid Tear Strength MD	ASTM D-4533	lbs (kg)	14.3 (6.48)
Trapezoid Tear Strength TD	ASTM D-4533	lbs (kg)	19.6 (8.89)
Wide Width Tensile MD	ASTM D-4595	lbs (kg)	109 (49.44)
Wide Width Tensile TD	ASTM D-4595	lbs (kg)	160 (72.57)
Elongation at Break MD	ASTM D-4595	percent	14%
Elongation at Break TD	ASTM D-4595	percent	26%
Puncture Resistance	ASTM D-4833	lbs (kg)	55.5 (25.17)
Bursting Strength	ASTM D-3786	lbs/in2 (kg/cm2)	176 (12.37)
Hydrocarbon Capacity		gal/yd2 (l/m2)	2.5 (11.3)



HalenHardy®, LLC
305 Main Street
Bellwood, PA, USA 16617

sales@HalenHardy.com
www.HalenHardy.com
814-822-2004